

US007094326B2

# (12) United States Patent

Crocker et al.

### (10) Patent No.: US 7,094,326 B2

(45) **Date of Patent:** \*Aug. 22, 2006

## (54) ELECTRODES FOR MICROFLUIDIC APPLICATIONS

(75) Inventors: Robert W. Crocker, Fremont, CA

(US); Cindy K. Harnett, Livermore, CA (US); Judith L. Rognlien,

Livermore, CA (US)

(73) Assignee: Sandia National Laboratories,

Livermore, CA (US)

(\*) Notice: Subject to any disclaimer, the term of this

patent is extended or adjusted under 35

U.S.C. 154(b) by 505 days.

This patent is subject to a terminal dis-

claimer.

(21) Appl. No.: 10/330,607

(22) Filed: Dec. 24, 2002

(65) Prior Publication Data

US 2004/0118689 A1 Jun. 24, 2004

(51) Int. Cl.

**G01N 27/453** (2006.01) **B28B 1/44** (2006.01)

(52) **U.S. Cl.** ...... **204/600**; 204/280; 264/42

#### (56) References Cited

#### U.S. PATENT DOCUMENTS

3,843,400 A *	10/1974	Radford et al 429/152
5,556,580 A *	9/1996	Suddith 264/4.3
6,277,257 B1*	8/2001	Paul et al 204/450
6,675,660 B1*	1/2004	Mosier et al 73/861.07
6,890,409 B1*	5/2005	Woudenberg et al 204/242

<sup>\*</sup> cited by examiner

Primary Examiner—Kaj K. Olsen (74) Attorney, Agent, or Firm—Donald A. Nissen

#### (57) ABSTRACT

An electrode device for high pressure applications. These electrodes, designed to withstand pressure of greater than 10,000 psi, are adapted for use in microfluidic devices that employ electrokinetic or electrophoretic flow. The electrode is composed, generally, of an outer electrically insulating tubular body having a porous ceramic frit material disposed in one end of the outer body. The pores of the porous ceramic material are filled with an ion conductive polymer resin. A conductive material situated on the upper surface of the porous ceramic frit material and, thus isolated from direct contact with the electrolyte, forms a gas diffusion electrode. A metal current collector, in contact with the gas diffusion electrode, provides connection to a voltage source.

#### 16 Claims, 1 Drawing Sheet

